



PAGEL®-FAST SETTING REPAIR-MORTAR

PROPERTIES

- is the permanent solution for quick **repair work** for concrete and mortar surfaces
- can be loaded after **2 hours** (and develops high early and final compressive strengths – it is **chloride and alumina free**)
- is cost effective by reducing closure times on concrete roads and pavements
- has good workability, high adhesive strength to cement based substrates and is highly resistant to abrasion
- is resistant to frost and dew-salt, water-impermeable, largely impervious to oil
- by modifying the water ratio a plastic to stiff consistency may be obtained – it is also supplied with steel fibre, basalt sand and various sizes of aggregate for different height applications
- is pre-mixed, only the addition of water for site use is necessary – no other primer systems are required

FIELDS OF APPLICATION

- **patching** concrete, screeding and plaster or stucco repairing holes, corners and cracks
- **grouting** masonry, floor and butt joints – laying materials (bricks, slabs, tiles etc.)
- **applying** binder layers and sprayed concrete
- **joining** prefabricated concrete components, old and new concrete
- **sealing** against water ingress by plastering, repairing and slurry sealing

Exposition category according to:
DIN 1045-2 / EN 206-1
PAGEL – RAPID REPAIR MORTAR

	XO 0	XC 1 2 3 4	XD 1 2 3	XS 1 2 3	XF 1 2 3 4	XA 1 2 3	XM 1 2 3
R 20/02	•	• • • • •	• •		• •	•	•
R 20/05	•	• • • • •	• • • • •	• • • • •	• • • • •	• • • • •	• •
R 20/20	•	• • • • •	• • • • •	• • • • •	• • • • •	• • • • •	• • • • •
R 20/40	•	• • • • •	• • • • •	• • • • •	• • • • •	• • • • •	• • • • •
R 20/80	•	• • • • •	• • • • •	• • • • •	• • • • •	• • • • •	• • • • •

R 20/02^{US}

R 20/05^{US}


R 20/20^{US}

R 20/40^{US}

R 20/80^{US}



R 20/02-
R 20/80



R 20/40



PAGEL®-FAST SETTING REPAIR-MORTAR

R 20/02 US

R 20/05 US

R 20/20 US

R 20/40 US

R 20/80 US

TECHNICAL DATA

TYPE		R 20/02	R 20/05	R 20/20	R 20/40	R 20/80
grain size	inch	0–0.01	0–0.02	0–0.08	0–0.16	0–0.31
coating thickness	inch	0.02–0.2	0.08–0.24	0.2–1.57	0.79–1.97	1.18–3.94
amount of water	%	max. 18	14–16	11–12	11–12	11–12
consumption	lbs/ft ³	118.62	112.37	124.86	124.86	124.86
density of freshly mixed mortar	lbs/ft ³	134.22	131.10	139.22	137.35	139.22
compressive strength*	2 h	PSI	≥ 725	≥ 725	≥ 725	≥ 725
	4 h	PSI	≥ 870	≥ 1,450	≥ 1,450	≥ 1,450
	8 h	PSI	≥ 1,450	≥ 1,885	≥ 2,175	≥ 2,175
	1 d	PSI	≥ 2,175	≥ 2,900	≥ 3,625	≥ 3,625
	7 d	PSI	≥ 4,350	≥ 5,800	≥ 5,800	≥ 5,800
	28 d	PSI	≥ 7,250	≥ 7,250	≥ 7,975	≥ 7,975
adhesive strength	28 d	PSI	≥ 290	≥ 290	≥ 290	≥ 290

All test data are guide values only.

* DIN EN 196-1-compliant compressive strength testing
DIN EN 12390-3-compliant compressive strength testing

working time: approx. 15 min. (676 °F)
amount required: approx. 2000 kg per m³ or 2 kg per l
supplied in: 25-kg-bags

storage: dry
shelf-life: 6 months in sealed bags

PROCESSING

SUBSTRATE: Concrete surfaces have to be cleaned and must be free of loose and unsound material, dust, oil, grease etc. – also of residual corrosion. If necessary the surface can be cleaned by scabbling or sandblasting. The repair area must then be wetted with water until surface saturation is reached.

MIXING: Depending on consistency required, measure out most of the total water requirement and place in mixer. Add R20 pre-mixed mortar to rotating mixer and allow to mix for short period. Add remainder of the water and allow to mix for a further 5 minutes.

ADHESION PRIMER: After cleaning, coat any exposed reinforcing steel with R 20/20 or R 20/10 corrosion protection or EH3 EPOXY RESIN (two coats sprinkled with quartz sand). Make up R 20 or R 20/10 as a slurry using the maximum water volume specified; brush this slurry thoroughly into the surface.

PROCESSING: Apply the mortar in the desired consistency, and before the adhesion primer dries out spread, compact and smooth the material. Keep all tools wet.

CAUTION: Protect exposed surfaces against wind, draughts and premature water evaporation e.g. with film or O1 PAGEL-SURFACE-PROTECTION

CE				
0921				
PAGEL® SPEZIAL-BETON GmbH & Co. KG, D-45355 Essen				
find the printed batch number				
0921 – BPR – 2034				
EN 1504-3:2005				
R 20 PAGEL® - RAPID REPAIR MORTAR				
Mortar for statically and not statically relevant repairs (on the basis of hydraulic cement)				
Product name:	R 20/02	R 20/05	R 20/20	R 20/40 R 20/80
Class:	R3		R4	
Compressive strength:	≥ 25 MPa		≥ 45 MPa	
Chloridion content:	≤ 0.05 %		≤ 0.05 %	
Adhesion:	≥ 1.5 MPa		≥ 2.0 MPa	
Prevented shrinkage/swelling:	≥ 1.5 MPa		≥ 2.0 MPa	
Resistance to carbonation:	NPD		NPD	
Modulus of elasticity:	≥ 15 GPa		≥ 20 GPa	
Temperature variation tolerance:	NPD			
Grip:	NPD			
Thermal expansion coefficient:	NPD			
Capillary water absorption:	NPD			
Reaction to fire:	Class A1			
Hazardous Substance:	In accordance with EN 1504-3:2005, 5.4			

NPD: „No Performance Determined“

The information provided in this leaflet, is supplied by our consulting service and is the end result of exhaustive research work and extensive experience. They are, however, without liability on our part, in particular with regard to third parties proprietary rights, and do not relieve the user of the responsibility for verifying that the products and processes are suitable for the intended application. The data presented was derived from tests under normal climate conditions according to DIN 50014 and mean average values and analysis. Deviations are possible when delivery takes place. Given that recommendations may differ from those shown in this leaflet written confirmation should be sought. It is the responsibility of the purchaser to ensure they have the latest leaflet issue and that its contents are current. Our customer service staff will be glad to provide assistance at any time. We appreciate the interest you have shown in our products. This technical data sheet supercedes previously issued information. Please find the latest leaflet issues at www.pagel.com.



PAGEL®-USA

4282 SHORELINE DRIVE · SPRING PARK
MINNESOTA 55384 · USA
OFFICE 001 952 942 6105 · FAX 001 952 942 6108
WWW.PAGEL-USA.COM · SALES@PAGEL-USA.COM