

PAGEL®

SPEZIAL-BETON



PAGEL® V B
MUNJEVITO PODLJEVNI MORT

PAGEL® V T
TURBO PODLJEVNI MORT

**POPRAVAK I POSTAVLJANJE POKLOPCA
REVIZIJSKOG OKNA (ŠAHTOVA)**



AKTUALNA IZDANJA TEHNIČKIH LISTOVA POTRAŽITE NA INTERNET STRANICI
WWW.PAGEL.COM

PAGEL-MUNJEVITO PODLJEVNI MORT

- operetivo nakon 30 minuta (pri 20°C)
- ekstremno visoka početna čvrstoća
- protočan i primjenjiv za popunjavanje
- ne steže se
- vodootporan
- otporan na mraz i otopne soli za posipavanje cesta

VB10: vrijeme obrade cca 10 minuta

VT10: vrijeme obrade cca 3 minute

- podljevanje poklopca revizijskog okna (šahtova)
- poklopci slivnika
- cijevi kanala
- instalaterski radovi
- stupovi i montažni dijelovi

	Granulacija mm	Visina podljeva mm	Tlačna čvrstoća				Čvrstoća na savijanje				Eks- panzija Vol. %	Potrošnja kg/m ³
			N/mm ²		N/mm ²		N/mm ²		N/mm ²			
			0,5 h	1 h	1 d	28 d	0,5 h	1 h	1 d	28 d		
VB10	0 – 1	10 – 50	≥ 5	≥ 8	≥ 35	≥ 60	-	-	-	-	+ 0,4	1900
VB40	0 – 4	30 – 60	≥ 5	≥ 8	≥ 35	≥ 60	-	-	-	-	+ 0,4	1900
VB-P10 (plastične)	0 – 1	10 – 50	≥ 5	≥ 8	≥ 35	≥ 55	-	-	-	-	+ 0,4	1800
VT10	0 – 1	10 – 50	≥ 5	≥ 8	≥ 45	≥ 70	≥ 2	≥ 2	≥ 5	≥ 8	+ 0,4	1900

Sve testne vrijednosti su okvirne vrijednosti, dokazane u našim njemačkim tvornicama, - vrijednosti iz drugih tvornica mogu odstupati.

